

Peth Head Office:
 21 Katanning Street
 Bayswater WA 6053
 Western Australia
 Phone: + 61 (0) 89379 1288
 Fax: +61 (0) 89379 1826

Kalgoorlie Office:
 Phone: +61 (0) 89091 1152
 Fax: +61 (0) 89091 1936
Johannesburg Office:
 Phone: +27 28 313 2845
 Mobile: +27 73 234 2845
 Fax: +27 28 313 2845
Accra office:
 Phone: +233 21939551
 Mobile: +233-244-213 496


ANFO Tube



Application:	For use as a semi-conductive transfer tube in pneumatic charging devices for explosive use.
Conductivity:	Minimum resistance of 0.015 MegaOhms / mtr. Maximum resistance of 2.0 MegaOhms / coil. As per AS2187.2 (tested as per BS2050)
Temperature:	-5°C to 60°C (23°F to 140°F)
Colour:	Black, smooth, with orange safety stripe
Specifications:	Manufactured to AS2187.2-1993 (tested as per BS2050)

Part No.	Description	ID (mm)	OD (mm)	Weight kg/mtr	Coil Length
05/100/01/124	Semi-Conductive, Semi-Rigid PVC	19.0	26.0	0.36	30
05/100/01/455	Semi-Conductive, Rigid Polyethylene	25.4	30.0	0.22	60
05/100/01/456	Semi-Conductive, Rigid Polyethylene	32.0	37.0	0.28	60

AG05



Note: We recommend that the user of this product be fully aware of the hazards as listed in section 4 of AS2187.2 before using this product in explosive applications.